



Linyi Aosen Chemical Co.,Ltd

ADD: NO.36 OF TONGDA RD., LANSHAN ECONOMIC DEVELOPMENT ZONE, LINYI, CHINA

TEL: 0086-539-7160368

FAX: 0086-539-8020962

Web: www.aoseneva.com

Email: susie@aosenchem.com



Polyvinyl Chloride

PVC S-60

Suggest use:

Rigid, half rigid products, transparent plate, panel, fittings, valves, injection molding parts, container, etc

Specification:

Item	Test condition	Test method	Data	Unit
Apparent density	---	GB/T3402-1994	0.53-0.61	g/ml
Viscosity	---	GB/T5761-1993	87-95	ml/g
Impurities particle	---	GB9348-1988	≤16	piece
Volatile (include water) content	---	GB/T2914-1999	≤0.30	%
Residue on sieve	0.25mm	GB/T2916-1997	≤1	%
Residue on sieve	0.063mm	GB/T2916-1997	≥93	%
Fisheye	---	GB/T4611-1993	≤20	piece/400cm ²
Residue vinyl chloride content	---	GB/T4615-1984	≤3	ppm
Plasticizer Absorptive capacity of 100g polymer	---	GB/T3400-2002	≥16	g