


## SUNNYJOINT MBT(M)

促进剂	Accelerator	
化学名称	Chemical Name	2-巯醇基苯并噻唑 2-Mercaptobenzothiazole
分子式	Molecular Formula	C <sub>7</sub> H <sub>5</sub> NS <sub>2</sub>
结构式	Molecular Structure	



分子量	Molecular Weight	167.26
比重	Gravity	1.42
CAS 编号	CAS NO.	149-30-4
产品规格	Specification	

外观	Appearance	粉末	油处理粉末	颗粒
		Powder	Oil-coated Powder	Granule
		淡黄色/Light Yellow		
初熔点	Initial M.P. °C ≥	169.0	169.0	169.0
加热减量	Loss on Drying % ≤	0.30	0.40	0.30
灰份	Ash % ≤	0.30	0.40	0.30
筛余物(150µm)	Residues(150µm) % ≤	0.10	0.10	--
油含量	Oil Content %	--	1.0-2.0	--

**性状** 易溶于乙酸乙酯、丙酮，溶于二氯甲烷、乙醚、氯仿、乙醇等有机溶剂和碱及碱性碳酸盐溶液，微溶于苯，不溶于水和汽油。

**Properties** Easily soluble in ethyl acetate, acetone, soluble in dichloromethane, ether, chloroform, ethanol and alkali and alkaline carbonate solution, slightly soluble in benzene, insoluble in water and petrol.

**用途** 通用型促进剂，广泛用于各种橡胶，对天然胶和一般硫磺化合物成胶具有快速促进作用，亦可用作化学增塑剂。有苦味不易用于制造与食品接触的橡胶制品。主要用于制造内胎、胶带、胶鞋和工业制品等。

**Uses** This is a common accelerator, widely used for varieties of rubbers, it has fast acceleration effect on natural rubber and regular vulcanized synthesis rubber, also could be used as a peptizer. It is bitter, not suitable for the rubber products contacting with food. Mainly used for the manufacturing of tire tube, rubber tape, shoes and industrial products.

**包装** 25 千克/袋  
**保质期** 24 个月

**Package** 25kg/bag  
**Storage Life** 24 month